

**CERTIFICATE OF ANALYSIS**

**CERTIFICATE NO.** 1004081.31/682

**CUSTOMER**

**CUSTOMER REF.** 06/340

BioCote Ltd  
 Wolverhampton Science Park  
 Technology Centre  
 Glaisher Drive  
 Wolverhampton  
 WV10 9RU

**SAMPLE DETAILS**

**DATE RECEIVED** 12/05/2006

N C BROWNS

**ORDER NO.**

METHOD: Determination of Antibacterial Activity using Test Based on JIS Z 2801: 2000

**DATE ANALYSED** 17/05/2006

**DATE REPORTED** 19/05/2006

**RESULTS (AS CFU CM<sup>-2</sup>)**

SAMPLE	SPECIES	CONTACT TIME		REDUCTION (CONTROL) %
		0 hrs	24 hrs	
POWDER COATING	E coli	2.3E+03	4.4E+05	
GREY METAL PLATES (POWDER COATING)	E coli	2.3E+03	3.2E+01	≥ 99.99%
POWDER COATING	MRSA	2.5E+03	1.1E+03	
GREY METAL PLATES (POWDER COATING)	MRSA	2.5E+03	< 11.11	≥ 99.02%

The above data shows the change in population following contact with the surface of the samples listed for 24 hours at 35°C under a RH of > 95%

INDUSTRIAL MICROBIOLOGICAL SERVICES LTD  
 PALE LANE  
 HARTLEY WINTNEY  
 HANTS  
 RG27 8DH  
 UK

Peter D Askew  
 Managing Director

